



# Novel Copolymer Cationic from Agroindustrial Waste using Microwave

Prayudhy Yushananta<sup>1,2\*</sup>, Mei Ahyanti<sup>1</sup>

<sup>1</sup>Department of Environmental Health, Politeknik Kesehatan Kemenkes Tanjungkarang, Lampung, Indonesia; <sup>2</sup>Doctoral Program of Environmental Science, Universitas Lampung, Lampung, Indonesia

## Abstract

**Edited by:** Sasho Stoleski  
**Citation:** Yushananta P, Ahyanti M. Novel Copolymer Cationic from Agroindustrial Waste using Microwave. Open Access Maced J Med Sci. 2022 Mar 25; 10(E):458-464. https://doi.org/10.3889/oamjms.2022.8126  
**Keywords:** Coagulation-flocculation; Banana pith; Turbidity; COD; Color  
**\*Correspondence:** Prayudhy Yushananta, Department of Environmental Health, Politeknik Kesehatan Kemenkes Tanjungkarang, Lampung, Indonesia. E-mail: prayudhyyushananta@gmail.com  
**Received:** 30-Nov-2021  
**Revised:** 23-Feb-2022  
**Accepted:** 24-Mar-2022  
**Copyright:** © 2022 Prayudhy Yushananta, Mei Ahyanti  
**Funding:** This research did not receive any financial support  
**Competing Interests:** The authors have declared that no competing interests exist  
**Open Access:** This is an open-access article distributed under the terms of the Creative Commons Attribution-NonCommercial 4.0 International License (CC BY-NC 4.0)

**BACKGROUND:** A cationic copolymer has been developed to substitute synthetic coagulants, resulting in decreased pH, potential health problems, high costs, and large sludge volumes.

**AIM:** This study evaluated the potential of banana pith in several treatments as a natural coagulant to reduce turbidity, COD, and color.

**METHODS:** The synthesis was carried out by inserting the cationic moiety of GTA into the starch backbone by microwave radiation. The cationic performance was tested four times, with a factorial design based on dose (4 levels), stirring speed (3 levels), and stirring time (3 levels). A two-way ANOVA test was applied to determine the effect of treatment.

**RESULTS:** The results showed that the cationic polymer could reduce turbidity (94.4%), COD (19.4%), and color (87.5%). Although all variables showed a significant effect ( $p < 0.05$ ), the use of 300 mg/L dose, stirring speed (200 rpm), for 5 min showed the highest reduction effect.

**CONCLUSIONS:** Using GTA and microwaves, banana pith starch can be modified into an effective cationic copolymer for water and wastewater treatment.

## Introduction

Water supply is intended to carry out their activities as humans [1]. Two serious problems increase the need for clean water, namely, population growth and rapid industrialization growth [2], [3], [4], [5], [6], [7], [8]. It is estimated that global water demand will increase to meet the needs of 9.7 billion people by 2050, from 7.7 billion in 2020 [9]. In the industrial sector, clean water is needed to reach about 22% of the total water available [10]. On the water supply aspect, the problems are the increase in water pollution from various toxic pollutants from industrial and domestic [4], [5], [7], [11], [12], [13], [14], [15]. Domestic wastewater mainly contains pathogenic microbiological, such as Coliform, *E. coli*, *Streptococcus sp.*, *Pseudomonas sp.*, *Vibrio sp.*, *Clostridia sp.*, *Arcobacter sp.*, *Thiobacillus sp.* [16], [17]. Meanwhile, the industrial wastewater is hydraulic overload, extreme temperatures, oil and grease, acids or bases, suspended solids, inorganic or organic, toxic and volatile materials, odors, or corrosive gases [4], [5], [7], [11], [12], [13], [14], [15].

These two problems encourage massive groundwater exploitation [15], [18]. Resulting in a reduced volume of groundwater storage, land subsidence, negative impacts on water supply, decreased surface water flow and loss of springs, and loss of wetlands, thus threatening to threaten the sustainability of water

supply [19], [20]. Globally, it estimated a reduction in groundwater from 1900 to 2008 of 4.500 km<sup>3</sup> (the equivalent of a sea-level rise of 12.6 mm). Since about 1950, the rate of groundwater reduction has increased significantly, averaging about 145 km<sup>3</sup>/year (equivalent to 0.40 mm/year of level increase) [19], [21].

Water treatment is the most rational choice to solve the demand and supply of clean water problems, in addition to efforts to diversify sustainable water sources (including the use of rainwater and seawater desalination) [1], [22]. Many technologies have been developed to treat water and wastewater, such as precipitation, adsorption, coagulation, flotation, ion exchange, membrane filtration, and biological and electrolytic methods have been used to remove particles from water [23], [24], [25], [26], [27], [28], [29], [30], [31], [32], [33], [34], [35], [36]. However, coagulation and flocculation techniques are the most widely applied technology globally as a vital step in removing colloid particles, natural organic matter, microorganisms, and inorganic ions present in untreated water [15], [32], [34], [37], [38], [39], [40].

A coagulant is an essential material in the coagulation-flocculation process which refers to the agglomeration process of colloidal particles with an average size of 5–200 nm and small suspended solids in water influenced by several factors such as temperature, ionic strength, pH, type and dose of material, coagulant,

size and distribution type, concentration and properties of organic matter, and colloid particles in suspension [2], [7], [8], [12], [15], [24], [25], [27], [28], [37], [38], [39], [40], [41], [42], [43], [44], [45], [46], [47], [48].

Metal salts such as ferric chloride ( $\text{FeCl}_3$ ), aluminum sulfate ( $\text{Al}_2(\text{SO}_4)_3$ ), Pollyalluminium Chloride (PAC), Polyferrous sulfate (PFS), and poly ferric chloride (PFC) have been widely used to treat water and various wastewater [4], [12], [37], [49], [50]. Despite providing good performance in water treatment, the coagulants have several disadvantages such as reducing pH to acid, inefficiency in low temperatures, high cost of coagulants, large sludge volume, and accelerated pipe corrosion. In addition, it also potential causes of health problems (Alzheimer's disease, neurotoxic, and carcinogenic) [4], [11],[13], [29], [37], [46], [51], [52].

An alternative is needed to overcome them: to use plant-based coagulants because they are not toxic or corrosive [5], [8], [11], [47], [49], [53], [54], [55], [56]. Several natural polyelectrolytes have been studied as coagulants or flocculants in water and wastewater treatment with varying results, including rice bagasse [57] *Tamarindus indica* [58], *Moringa aoleifera* [59], *Manihot esculenta* [60], *Cactus opuntia* [61], and *Dolichos lablab* [62]. The advantages of using organic polyelectrolytes include using a lower coagulant dose, a smaller increase in ionic load on treated water, a decrease in the aluminum content in treated water, and cost savings [32], [63].

Agricultural waste that has not been widely studied as raw material for natural coagulants is banana stem waste, even though it is very potential because of its abundant and sustainable post-harvest availability [15], [32], [37], [38], [64]. The main ingredients in banana pith are water, fiber, and polysaccharides or starch. The composition of C, H, O as much as 33.2%; 0.49%; and 6.17% [64], other studies mention 32.3% carbon, 4.21% hydrogen, 1.46% nitrogen, 43.5% oxygen, and 0.86% sulfur [32].

Polysaccharides are usually modified by conventional redox grafting methods [24], [65], [66], [67]. Microwave radiation can be used in starch modification based on the advantages of energy-saving and speed [68], [69], [70]. This study synthesized starch from banana pith through a copolymerization process using the microwave method. Furthermore, the flocculation performance was studied. This study aimed to obtain a natural coagulant modified from agricultural waste to reduce turbidity, chemical oxygen demand (COD), and color.

## Materials and Methods

This study was conducted using the Way Kuripan River water which is the source of raw water for drinking water treatment (Figure 1). The water sample was dosed with natural coagulant followed by rapid

mixing, flocculation, and sedimentation. The efficiency of removing contaminants is calculated by reducing turbidity, COD, and color. Banana pith is obtained from cavendish (*Musa paradisiaca*) harvested in Central Lampung Regency, Lampung Province.




Figure 1: Sampling coordinates (-5.4373308, 105.2515303)

GTA (3-Chloro-2-hydroxypropyl trimethyl ammonium chloride), sodium hydroxide, and ethanol were obtained from Sigma-Aldrich. All these reagents were of analytical grade and were applied directly. All solutions were prepared with deionized water. An Electrolux (Model No. EMM20M38GW) domestic microwave oven was used for the experiment.

### Water sampling

Samples were collected from the Way Kuripan River in pre-cleaned containers (Figure 1). The samples were stored in a cool box and transported to the laboratory, sampling using the Standard Method [71].

### The starch of banana pith

Banana pith cleaned and rinsed with clean water and cut into small pieces. Soak with 0.5% Sodium Metabisulfite ( $\text{Na}_2\text{S}_2\text{O}_5$ ) solution for 15 min to stop the browning effect. Maceration (grated). Squeezed and filtered (0.4 mm) was performed to separate the liquid from the pulp. Do sedation so that the starch settles, the water is removed. Rinse the sediment with distilled water to clean the starch from the fibers. Dry in the oven at  $80^\circ\text{C}$  until dry. Milling and shifting to get banana pith starch flour storage of banana pith flour in a desiccator to avoid additional moisture content.

### Synthesis of natural coagulant with microwave radiation

Typically, 1.50g GTA (3-Chloro-2-hydroxypropyl trimethyl ammonium chloride) was added to a 100 mL container containing 5 mL sodium hydroxide (0.10 g/mL) aqueous. The solution was stirred thoroughly for 10 min. 10.00 g of starch is added to the mixture. Stirring was continued for 30 min on a water bath at  $500^\circ\text{C}$ . Then, microwave irradiation was performed. Microwave

irradiation (480 watts) has for 5 min at regular intervals. The microwave irradiation cycle is carried out to prevent the temperature from rising above 50°C. The reaction vessel and its contents were cooled to room temperature. The precipitate is left in the reaction vessel and washed (3 times) with ethanol. Dry in an oven at 50°C for 6 h to obtain cationic starch.

### Coagulant-flocculation test

Coagulation and flocculation tests were performed on water samples from the Way Kuripan River using the Jar-Test. 500 mL river water was transferred to a 1000 ml beaker glass and placed in a jar-testing device. An initial pH check was performed, and all experiments were carried out at room temperature.

The desired amount of coagulant (Table 1) was added to the sample water and stirred at three variations of speed (rotary per minute) and time (minute), followed by slow stirring at 30 rpm for 15 min. The mixture was left for 30 min to settle. The formation of flock particles was observed and recorded. Samples were taken with a pipette from a depth of 2 cm to determine turbidity, COD, and color. All analyses were performed in quadruplicate.

**Table 1: Dose of coagulant, speed, and time tested**

Dose (mg/L)	Speed (rpm)	Time (min)
50	150	2
100	180	3
200	200	5
300		

### Analysis water samples

The turbidity test used a portable turbidimeter (Model HACH 2100P). The principle of measuring turbidity is the ratio of the light intensity scattered by the sample. The sample is placed into the turbidimeter, and the turbidity value is shown in NTU units. The total percentage of turbidity removal is calculated:

$$\text{Total turbidity percentage removal} = \frac{A - B}{A} \times 100 \quad (1)$$

where  $A$  is the initial water turbidity (NTU).  $B$  is the turbidity after treatment (NTU).

The color test used a colorimeter (model HANNA HI96727). The principle of measuring color is that the amount of light absorbed by a solution is directly proportional to the concentration and width of the solution through which the light passes. The degree of color is determined colorimetrically, with units of TCU (True Color Unit). The total percentage of color removal is calculated:

$$\text{Total color percentage removal} = \frac{A - B}{A} \times 100 \quad (2)$$

where  $A$  is the initial water color (TCU).  $B$  is the color after treatment (TCU).

The COD test was measured using UV Spectrophotometer HACH model. COD refers to the amount of oxygen required to oxidize the organic compounds in a water sample to carbon dioxide and water. COD percentage removal was calculated as follows:

$$\text{COD percentage removal} = \frac{A - B}{A} \times 100 \quad (3)$$

where  $A$  is the COD of row water (mg/L),  $B$  is COD after treatment (mg/L).

### Statistical analysis

Data were analyzed to determine the individual and combination effects of the research variables (dose, speed, and time) used a two-way analysis of variance (ANOVA) overall analysis at 95% confidence level.

## Results and Discussion

### Characteristic of natural coagulant

The copolymer is synthesized with microwave power (480 watts). The mechanism of microwave-assisted grafting is as follows: The microwave radiation rotates the GTA molecules, leading to the severing of its epoxy propyl bond, and the pi bond electron cloud splits up into two localized clouds (i.e., free radical sites on the constituent carbon atoms) [68], [69]. Moreover, the polar groups absorb the microwave (e.g., OH groups attached to the starch molecule). Then behave as if they were anchored to an immobile raft. Its immobile localized rotations will occur in the microwave region [68], which eventually leads to the severing of these bonds, forming free radical sites. The free radical sites created on the starch backbone and the GTA interact to yield the cationic graft copolymer through the usual free radical reaction mechanism.

Table 2 shows the high levels of amylopectin in banana pith starch. The grafting of positive ions into amylopectin will produce a more effective polymer because of the dangling polymer chains and highly branched structure [68], [72]. The results of the synthesis gave a decrease in amylopectin by 9.87%. It indicates the occurrence of polymer chain termination due to microwave irradiation.

**Table 2: Characteristics of banana pith starch**

Characteristic	Starch (%)	Amyloza (%)	Amylopectin (%)
Row starch	47.57	22.95	77.05
Syntesis starch	36.46	30.56	69.44

### Treatment of water using natural coagulant

In general, the water quality of the Way Kuripan river shows that it does not meet the quality requirements for drinking water sources (Table 3). Water has significant turbidity, COD, and color values.

Coagulation and flocculation of river water with natural coagulant showed a decrease of 94.4, 19.4, and 87.5% of turbidity, COD, and color (Table 4). Even though the quality standards of clean water and drinking water have been achieved, the use of natural coagulants has significantly reduced turbidity, COD, and color.

### **Effect of natural coagulant on the removal turbidity, COD, and color**

Table 4 shows the significant effect of dose on the decrease in turbidity and color ( $p < 0.05$ ). Similarly, the effect of stirring speed and stirring time also significantly affected turbidity and color ( $p < 0.05$ ). The combination of treatments was also observed in the experiment. A significant effect was found in all treatment combinations on turbidity ( $p < 0.05$ ). In color, the significant effect is only shown in the combination of speed and time.

**Table 3: Water quality (pre and post) treatment using natural coagulant**

Quality parameters	Row water	Treated water	Removal (%)	Guidelines for	
				Clean water	Drinking water
Turbidity (NTU)	563.0	31.4	94.4	25	5
COD (mg/L)	43.2	32.8	19.4	-	-
Color (TCU)	1900.0	238.2	87.5	50	15

COD: Chemical oxygen demand.

These results indicate that the dose and time of stirring are essential in the flocculation process.

The main mechanisms of the flocculation process of plant-based coagulants are neutralization and bridging [37], [73]. This mechanism begins with the adsorption process of polymer coagulant particles [15], [28], [34], [39], [55]. Bridging usually occurs when long-chain polymers are adsorbed on the particles and leave the coagulant polymer segments to bridge the particles. The high molecular weight is advantageous for the bridging mechanism. The bridging mechanism forms strong clumps, even at elevated agitation. However, irreversible flock damage can occur due to polymer friction under turbulent conditions. Dose plays a vital role in the bridging mechanism. However, at higher doses, the colloidal particles are stabilized due to the steric repulsion of the polymer covering the particles. Meanwhile, there is not enough polymer chain at low doses to form a bridge [37], [40], [61], [73], [74], [75].

Neutralization occurs when the oppositely charged coagulant polymer is adsorbed on the particle surface, thereby neutralizing the charge of the

colloidal particles. A high charge density coefficient with low molecular weight will effectively coagulation performance. The reduction in the surface charge of the particles results in a decrease in the electrostatic repulsion between the colloidal particles, thereby enabling coagulation [37], [40], [53], [76].

The raw water quality becomes very important to determine the coagulant dose required [68], [72]. The higher the colloid content, the higher the dose required. However, on the other hand, flocculation cannot exceed the optimum dose, and subsequent additions result in lower efficiency. It is explained that there are no more free particle surfaces available for installation. Hence, it takes the correct dose in water treatment using the flocculation method [28], [68], [77].

Although the removal effect was lower than similar studies, it was due to the different raw water quality. Alwi *et al.* [64] used a 33.3% dose to reduce 98.5% turbidity (81.3 to 1.2 NTU), and 80.1% COD (152.4 to 30.3 mg/L). Kakoi *et al.* [32] used a dose of 0.1 kg/M<sup>3</sup> to reduce 98.6% turbidity (279.0 to 4.0 NTU), and 73.0% COD (160.0 to 73.0 mg/L). Villabona *et al.* [78] reduced turbidity by 76.5% (32.3 to 7.6 NTU) at a dose of 33.3%. Meanwhile, the turbidity of the raw water in the study was 563.0 NTU. The high turbidity of the raw water results in a lower removal effect. This factor also occurs in COD.

Figure 2 shows the change in the value of each parameter based on dose, stirring speed, and stirring time. In various doses, the highest reduction effect was at a dose of 300 mg/L, and the lowest was at 50 mg/L. Stirring speed gives the most significant effect at 200 rpm and the smallest at 150 rpm. The stirring time gives the best-removing effect of 5 min. These results explain that the higher the dose used, the higher the reduction effect. It is related to the number of cations available for the bridging mechanism to occur correctly. Stirring speed aims to accelerate the reaction between coagulant and colloid in water. The stirring time is related to the length of flocculation through the bridging mechanism.

However, coagulation/flocculation is a unique process, and the three variables are interrelated. Excessive doses cause stabilization of colloidal particles resulting in steric repulsion from the polymer covering the particles. On the other hand, if the dose is low, there is not enough polymer chain to form a bridge. High speed for a long time causes turbulence, resulting in the rupture of the flock formed. For this reason, Jar

**Table 4: Statistical analysis (two-ways analysis of variance)**

Source	Turbidity		COD		Color	
	Sum of squares	Significant	Sum of squares	Significant	Sum of squares	Significant
Corrected model	6867.81	0.000	435.93	0.844	357822.18	0.000
Intercept	142380.44	0.000	174842.45	0.000	8178170.06	0.000
Dose	1138.25	0.000	33.32	0.578	26915.74	0.004
Speed	217.60	0.007	36.04	0.346	40823.04	0.000
Time	1252.53	0.000	0.73	0.979	80201.79	0.000
Dose × speed	404.21	0.005	72.61	0.634	11313.56	0.440
Dose × time	512.42	0.001	55.36	0.770	22894.81	0.073
Speed × time	2533.91	0.000	58.23	0.487	154303.16	0.000
Dose × speed × time	808.87	0.000	179.62	0.559	21370.05	0.522
Error	2228.32		1815.53		207176.75	

COD: Chemical oxygen demand.




Figure 2: Effect of natural coagulant on the removal turbidity, COD, and color by dose (a), speed (b), and time (c)

Test is needed to get the optimum dose, speed, and time. In this study, the highest reducing effect was at a dose of 300 mg/L, stirring speed of 200 rpm, for 5 min.

## Conclusion

A new copolymer coagulant has been synthesized from banana agricultural waste using microwave radiation. The performance of the copolymer was able to remove turbidity (94.4%), COD (19.4%), and color (87.5%). The highest reducing effect was at a dose of 300 mg/L, stirring speed of 200 rpm, for 5 min. This experimental study has proven that natural polysaccharides can be modified by grafting cations

into the backbone to be used as effective coagulants for treating water.

## Author Contributions

All the authors contributed equally to the preparation, development, and completion of this manuscript.

## Ethics

This article is original and contains unpublished material. The corresponding author confirms that the other authors have read and approved the manuscript and that there were no ethical issues involved.

## References

- Garcia Soler N, Moss T, Papisozomenou O. Rain and the city: Pathways to mainstreaming rainwater harvesting in Berlin. *Geoforum*. 2018;89:96-106. <https://doi.org/10.1016/j.geoforum.2018.01.010>
- Hakizimana JN, Gourich B, Chafi M, Stiriba Y, Vial C, Drogui P, *et al*. Electrocoagulation process in water treatment: A review of electrocoagulation modeling approaches. *Desalination*. 2017;404:1-21. <https://doi.org/10.1016/j.desal.2016.10.011>
- Bhatnagar A, Sillanpää M. Utilization of agro-industrial and municipal waste materials as potential adsorbents for water treatment-A review. *Chem Eng J*. 2010;157:277-96. <https://doi.org/10.1016/j.cej.2010.01.007>
- Choy SY, Prasad KM, Wu TY, Raghunandan ME, Ramanan RN. Utilization of plant-based natural coagulants as future alternatives towards sustainable water clarification. *J Environ Sci (China)*. 2014;26(11):2178-89. <https://doi.org/10.1016/j.jes.2014.09.024>  
PMid:25458671
- Asrafuzzaman M, Fakhruddin AN, Hossain MA. Reduction of turbidity of water using locally available natural coagulants. *ISRN Microbiol*. 2011;2011:632189. <https://doi.org/10.5402/2011/632189>  
PMid:23724307
- Quince E. Summary of Indonesia's Agriculture, Natural Resources, and Environment Sector Assessment. *ADB Papers On Indonesia*; 2015. p. 1-7.
- Carolin CF, Kumar PS, Saravanan A, Joshiba GJ, Naushad M. Efficient techniques for the removal of toxic heavy metals from aquatic environment: A review. *J Environ Chem Eng*. 2017;5:2782-99. <https://doi.org/10.1016/j.jece.2017.05.029>
- Kumar PS, Joshiba GJ, Femina CC, Varshini P, Priyadarshini S, Karthick MS, *et al*. A critical review on recent developments in the low-cost adsorption of dyes from wastewater. *Desalination Water Treatment*. 2019;172:395-416. <https://doi.org/10.5004/dwt.2019.24613>

9. UN. World Population Prospects 2019: Highlights United Nations. United Nation; 2020.
10. Arnel NW. Climate change and global water resources. *Global Environ Change*. 1999;9:S31-49. [https://doi.org/10.1016/S0959-3780\(99\)00017-5](https://doi.org/10.1016/S0959-3780(99)00017-5)
11. Taiwo AS, Adenike K, Aderonke O. Efficacy of a natural coagulant protein from *Moringa oleifera* (Lam) seeds in treatment of Opa reservoir water, Ile-Ife, Nigeria. *Heliyon*. 2020;6:e03335. <https://doi.org/10.1016/j.heliyon.2020.e03335>  
PMid:32051883
12. Salehizadeh H, Yan N, Farnood R. Recent advances in polysaccharide bio-based flocculants. *Biotechnol Adv*. 2018;36(1):92-119. <https://doi.org/10.1016/j.biotechadv.2017.10.002>  
PMid:28993221
13. Walton JR. Aluminum's involvement in the progression of Alzheimer's disease. *J Alzheimers Dis*. 2013;35(1):7-43. <https://doi.org/10.3233/JAD-121909>  
PMid:23380995
14. Wang Y, Jiang L, Shang H, Li Q, Zhou W. Treatment of azo dye wastewater by the self-flocculating marine bacterium *Aliiglaciecola lipolytica*. *Environ Technol Innov*. 2020;19:100810. <https://doi.org/10.1016/j.eti.2020.100810>
15. Ahmad T, Danish M. Prospects of banana waste utilization in wastewater treatment: A review. *J Environ Manag*. 2018;206:330-48. <https://doi.org/10.1016/j.jenvman.2017.10.061>  
PMid:29100146
16. Sumampouw OJ, Risjani Y. Bacteria as indicators of environmental pollution: Review. *Int J Ecosyst*. 2014;4:251-8. <https://doi.org/10.5923/j.ije.20140406.03>
17. Yushananta P, Bakri S. Analysis for increasing access to safe drinking water and healthy sanitation using a cost benefit analysis (CBA) approach. *J Kesehatan*. 2021;12:306. <https://doi.org/10.26630/jk.v12i2.1855>
18. Tamaddun K, Kalra A, Ahmad S. Potential of rooftop rainwater harvesting to meet outdoor water demand in arid regions. *J Arid Land*. 2018;10:68-83. <https://doi.org/10.1007/s40333-017-0110-7>
19. Mays LW. Groundwater resources sustainability: Past, present, and future. *Water Resour Manag*. 2013;27:4409-24. <https://doi.org/10.1007/s11269-013-0436-7>
20. Konikow LF, Kendy E. Groundwater depletion: A global problem. *Hydrogeol J*. 2005;13:317-20. <https://doi.org/10.1007/s10040-004-0411-8>
21. Konikow LF. Contribution of global groundwater depletion since 1900 to sea-level rise. *Geophys Res Lett*. 2011;38:48604. <https://doi.org/10.1029/2011GL048604>
22. Sánchez AS, Cohim E, Kalid RA. A review on physicochemical and microbiological contamination of roof-harvested rainwater in urban areas. *Sustain Water Qual Ecol*. 2015;6:119-37. <https://doi.org/10.1016/j.swaqe.2015.04.002>
23. Abdulfatai J, Saka AA, Afolabi AS, Micheal O. Development of adsorbent from banana peel for wastewater treatment. *Appl Mech Mater*. 2013;248:310-5. <https://doi.org/10.4028/www.scientific.net/AMM.248.310>
24. Barbosa AD, da Silva LF, de Paula HM, Romualdo LL, Sadoyama G, Andrade LS. Combined use of coagulation (*M. oleifera*) and electrochemical techniques in the treatment of industrial paint wastewater for reuse and/or disposal. *Water Res*. 2018;145:153-61. <https://doi.org/10.1016/j.watres.2018.08.022>
25. Shen X, Gao B, Guo K, Yue Q. Application of composite flocculants for removing organic matter and mitigating ultrafiltration membrane fouling in surface water treatment: the role of composite ratio. *Environ Sci Water Res Technol*. 2019;5:2242-50. <https://doi.org/10.1039/C9EW00528E>
26. Stavrinou A, Aggelopoulos CA, Tsakiroglou CD. Exploring the adsorption mechanisms of cationic and anionic dyes onto agricultural waste peels of banana, cucumber and potato: Adsorption kinetics and equilibrium isotherms as a tool. *J Environ Chem Eng*. 2018;6:6958-70. <https://doi.org/10.1016/j.jece.2018.10.063>
27. Wu H, Liu Z, Yang H, Li A. Evaluation of chain architectures and charge properties of various starch-based flocculants for flocculation of humic acid from water. *Water Res*. 2016;96:126-35. <https://doi.org/10.1016/j.watres.2016.03.055>
28. Yongabi K. Biocoagulants for water and waste water purification: A review. *Int Rev Chem Eng*. 2010;2:444-58.
29. Choudhary M, Neogi S. A natural coagulant protein from *Moringa oleifera*: Isolation, characterization, and potential use for water treatment. *Mater Res Exp*. 2017;4:1-27. <https://doi.org/10.1088/2053-1591/aa8b8c>
30. Ghimici L, Constantin M. A review of the use of pullulan derivatives in wastewater purification. *React Funct Polym*. 2020;149:104510. <https://doi.org/10.1016/j.reactfunctpolym.2020.104510>
31. de Gurgil DB, Cinelli LP, Simas NK, Pessoa A, Sette LD. Marine prebiotics: Polysaccharides and oligosaccharides obtained by using microbial enzymes. *Food Chem*. 2019;280:175-86. <https://doi.org/10.1016/j.foodchem.2018.12.023>
32. Kakoi B, Kaluli JW, Ndiba P, Thiong'o G. Banana pith as a natural coagulant for polluted river water. *Ecol Eng*. 2016;95:699-705. <https://doi.org/10.1016/j.ecoleng.2016.07.001>
33. Li Y, Liu J, Yuan Q, Tang H, Yu F, Lv X. A green adsorbent derived from banana peel for highly effective removal of heavy metal ions from water. *RSC Adv*. 2016;6:45041-8. <https://doi.org/10.1039/c6ra07460j>
34. Muthuraman G, Sasikala S. Removal of turbidity from drinking water using natural coagulants. *J Ind Eng Chem*. 2014;20:1727-31. <https://doi.org/10.1016/j.jiec.2013.08.023>
35. Radoiu M. Preparation of polyelectrolytes for wastewater treatment. *J Hazard Mater*. 2004;106:19-24. <https://doi.org/10.1016/j.jhazmat.2003.08.014>  
PMid:14693435
36. Salleh MA, Mahmoud DK, Karim WA, Idris A. Cationic and anionic dye adsorption by agricultural solid wastes: A comprehensive review. *Desalination*. 2011;280:1-13. <https://doi.org/10.1016/j.desal.2011.07.019>
37. Kristianto H. The potency of Indonesia native plants as natural coagulant: A mini review. *Water Conserv Sci Eng*. 2017;2:51-60. <https://doi.org/10.1007/s41101-017-0024-4>
38. Maurya S, Daverey A. Evaluation of plant-based natural coagulants for municipal wastewater treatment. *3 Biotech*. 2018;8:1-4. <https://doi.org/10.1007/s13205-018-1103-8>
39. Sillanpää M, Ncibi MC, Matilainen A, Vepsäläinen M. Removal of natural organic matter in drinking water treatment by coagulation: A comprehensive review. *Chemosphere*. 2018;190:54-71. <https://doi.org/10.1016/j.chemosphere.2017.09.113>
40. Tripathy T, De BR. Flocculation: A new way to treat the waste water. *J Phys Sci*. 2006;10:93-127.
41. Fu Y, Meng XJ, Lu NN, Jian HL, Di Y. Characteristics changes in banana peel coagulant during storage process. *Int J Environ Sci Technol*. 2019;16:7747-56. <https://doi.org/10.1007/s13762-018-02188-0>
42. Villabona-Ortiz A, Tejada-Tovar C, Toro RO. Comparative study of the use of starch from agroindustrial materials in the coagulation-flocculation process. *Rev Mex Ingenier Quím*. 2019;19:593-601. <https://doi.org/10.24275/rmiq/IA740>
43. O'Connell DW, Birkinshaw C, O'Dwyer TF. Heavy metal adsorbents prepared from the modification of cellulose: A review. *Bioresour Technol*. 2008;99:6709-24. <https://doi.org/10.1016/j.biortech.2008.01.036>
44. Jiraprasertkul W, Nuisin R, Jinsart W, Kiatkamjornwong S. Synthesis and characterization of cassava starch graft

- poly(acrylic acid) and poly[(acrylic acid)-co-acrylamide] and polymer flocculants for wastewater treatment. *J Appl Polym Sci*. 2006;102:2915-28. <https://doi.org/10.1002/app.23956>
45. Bolto BA. Soluble polymers in water purification. *Prog Polym Sci*. 1995;20:987-1041. [https://doi.org/10.1016/0079-6700\(95\)00010-D](https://doi.org/10.1016/0079-6700(95)00010-D)
  46. Yavuz CI, Vaizoğlu SA, Güler Ç. Aluminium in drinking water. *TAF Prev Med Bull*. 2013;12:589-96. <https://doi.org/10.5455/pmb.1-1345809534>
  47. Baptista AT, Silva MO, Gomes RG, Bergamasco R, Vieira MF, Vieira AM. Protein fractionation of seeds of *Moringa oleifera* lam and its application in superficial water treatment. *Sep Purif Technol*. 2017;180:114-24. <https://doi.org/10.1016/j.seppur.2017.02.040>
  48. Theodoro JD, Lenz GF, Zara RF, Bergamasco R. Coagulants and natural polymers: Perspectives for the treatment of water. *Plast Polym Technol*. 2013;2:55-62.
  49. Oladoja NA. Headway on natural polymeric coagulants in water and wastewater treatment operations. *J Water Proc Eng*. 2015;6:174-92. <https://doi.org/10.1016/j.jwpe.2015.04.004>
  50. De Carvalho HP, Huang J, Zhao M, Liu G, Dong L, Liu X. Improvement of Methylene Blue removal by electrocoagulation/banana peel adsorption coupling in a batch system. *Alexandria Eng J*. 2015;54:777-86. <https://doi.org/10.1016/j.aej.2015.04.003>
  51. Mouhamed Bayane B, Yanjun Q, Bekhzad Y. A review and analysis of railway transportation system in the economic community of West African States: Towards the development of sustainable regional goal. *Glob J Eng Technol Adv*. 2020;2020:11-022. <https://doi.org/10.30574/gjeta>
  52. Choubey S, Rajput SK, Bapat KN. Comparison of efficiency of some natural coagulants bioremediation. *Int J Emerg Technol Adv Eng*. 2012;2:429-34.
  53. Kalia S, Sabaa MW. Polysaccharide Based Graft Copolymers. Vol. 9783642365; 2013. <https://doi.org/10.1007/978-3-642-36566-9>
  54. Polaskova M, Peer P, Cermak R, Ponizil P. Effect of thermal treatment on crystallinity of poly(ethylene oxide) electrospun fibers. *Polymers*. 2019;11(9):1384. <https://doi.org/10.3390/polym11091384>
  55. Priyatharishini M, Mokhtar NM, Kristanti RA. Study on the effectiveness of banana peel coagulant in turbidity reduction of synthetic wastewater. *Int J Eng Technol Sci*. 2019;6:82-90. <https://doi.org/http://dxdoi.org/10.15282/ijets.6.1.2019.1007>
  56. Ibrahim A, Yaser AZ. Colour removal from biologically treated landfill leachate with tannin-based coagulant. *J Environ Chem Eng*. 2019;7:103483. <https://doi.org/10.1016/j.jece.2019.103483>
  57. Guo J, Chen C. Sludge conditioning using the composite of a bioflocculant and PAC for enhancement in dewaterability. *Chemosphere*. 2017;185:277-83. <https://doi.org/10.1016/j.chemosphere.2017.06.111>
  58. Mishra A, Bajpai M. Flocculation behaviour of model textile wastewater treated with a food grade polysaccharide. *J Hazard Mater*. 2005;118:213-7. <https://doi.org/10.1016/j.jhazmat.2004.11.003>
  59. Rodriño-Arguello JP, Feria-Diaz JJ, de Paternina-Urbe RJ, Marrugo-Negrete JL. Sinú River raw water treatment by natural coagulants. *Rev Facult Ingenier Univ Antioquia*. 2015;76:11. <https://doi.org/10.17533/udea.redin.n76a11>
  60. dos Santos JD, Veit MT, Juchen PT, da Cunha Gonçalves G, Palácio SM, Fagundes-Klen M. Use of different coagulants for cassava processing wastewater treatment. *J Environ Chem Eng*. 2018;6:1821-7. <https://doi.org/10.1016/j.jece.2018.02.039>
  61. Choudhary M, Ray MB, Neogi S. Evaluation of the potential application of cactus (*Opuntia ficus-indica*) as a bio-coagulant for pre-treatment of oil sands process-affected water. *Sep Purif Technol*. 2019;209:714-24. <https://doi.org/10.1016/j.seppur.2018.09.033>
  62. Daverey A, Tiwari N, Dutta K. Utilization of extracts of *Musa paradisiaca* (banana) peels and *Dolichos lablab* (Indian bean) seeds as low-cost natural coagulants for turbidity removal from water. *Environ Sci Pollut Res*. 2019;26:34177-83. <https://doi.org/10.1007/s11356-018-3850-9>
  63. Kakoi B, Kaluli JW, Ndiba P, Thiong'o G. Optimization of maerua decumbent bio-coagulant in paint industry wastewater treatment with response surface methodology. *J Cleaner Prod*. 2017;164:1124-34. <https://doi.org/10.1016/j.jclepro.2017.06.240>
  64. Alwi H, Idris J, Musa M, Ku Hamid KH. A preliminary study of banana stem juice as a plant-based coagulant for treatment of spent coolant wastewater. *J Chem* 2013;2013:165057. <https://doi.org/10.1155/2013/165057>
  65. Pal S, Ghosh S, Sen G, Jha U, Singh RP. Cationic tamarind kernel polysaccharide (Cat TKP): A novel polymeric flocculant for the treatment of textile industry wastewater. *Int J Biol Macromol*. 2009;45:518-23. <https://doi.org/10.1016/j.ijbiomac.2009.08.004>
  66. Yaman SB. Synthesis of Dicationic Ionic Liquids and their Application as Co-Catalyst for Fructose Conversion; 2018.
  67. Wan Ahmad WY. Synthesis and physicochemical characterization of cationic polymeric surfactant from *Dioscorea pyriformis* Starch. *Malaysian J Anal Sci*. 2016;20:1278-85. <https://doi.org/10.17576/mjas-2016-2006-06>
  68. Lin Q, Qian S, Li C, Pan H, Wu Z, Liu G. Synthesis, flocculation and adsorption performance of amphoteric starch. *Carbohydr Polym*. 2012;90:275-83. <https://doi.org/10.1016/j.carbpol.2012.05.035>
  69. Mishra S, Mukul A, Sen G, Jha U. Microwave assisted synthesis of polyacrylamide grafted starch (St-g-PAM) and its applicability as flocculant for water treatment. *Int J Biol Macromol*. 2011;48:106-11. <https://doi.org/10.1016/j.ijbiomac.2010.10.004>
  70. Wei Y, Cheng F, Zheng H. Synthesis and flocculating properties of cationic starch derivatives. *Carbohydr Polym*. 2008;74:673-9. <https://doi.org/10.1016/j.carbpol.2008.04.026>
  71. National Standardization Agency of Indonesia. Water and Waste Water. Sampling Method for Waste Water (SNI 6989.59-2008). Ch. 59. National Standardization Agency of Indonesia; 2008. p. 1-19.
  72. Bolto B, Gregory J. Organic polyelectrolytes in water treatment. *Water Res*. 2007;41:2301-24. <https://doi.org/10.1016/j.watres.2007.03.012>
  73. Yin CY. Emerging usage of plant-based coagulants for water and wastewater treatment. *Murdoch Univ*. 2010;45:1437-44. <https://doi.org/10.1016/j.procbio.2010.05.030>
  74. Amran AH, Zaidi NS, Muda K, Loan LW. Effectiveness of natural coagulant in coagulation process: A review. *Int J Eng Technol*. 2018;7:34. <https://doi.org/10.14419/ijet.v7i3.9.15269>
  75. Järnström L, Lason L, Rigdahl M. Flocculation in kaolin suspensions induced by modified starches 1. Cationically modified starch-effects of temperature and ionic strength. *Colloids Surf A Physicochem Eng Aspects*. 1995;104:191-205. [https://doi.org/10.1016/0927-7757\(95\)03270-5](https://doi.org/10.1016/0927-7757(95)03270-5)
  76. Duan J, Gregory J. Coagulation by hydrolysing metal salts. *Adv Colloid Interface Sci*. 2003;100-102:475-502. [https://doi.org/10.1016/S0001-8686\(02\)00067-2](https://doi.org/10.1016/S0001-8686(02)00067-2)
  77. Almonaitye K, Bendoraitiene J, Babelyte M, Rosliuk D, Rutkaite R. Structure and properties of cationic starches synthesized by using 3-chloro-2-hydroxypropyltrimethylammonium chloride. *Int J Biol Macromol*. 2020;164:2010-7. <https://doi.org/10.1016/j.ijbiomac.2020.08.089>
  78. Villabona-Ortiz A, Tejada-Tovar C, Toro RO. Comparative study of the use of starch from agro-industrial materials in the coagulation-flocculation process. *Rev Mex Ingenier Quím* 2020;12:505-11.